



automotive
metalized
 window film

MET
 Automotive Window Film

TOTAL SOLAR ENERGY	5%	18%	35%	50%
TRANSMITTED	27%	27%	36%	43%
REFLECTED	7%	8%	9%	11%
ABSORBED	63%	65%	55%	46%

VISIBLE LIGHT				
TRANSMITTED	5%	15%	32%	44%
REFLECTED	5%	5%	7%	9%
U.V. LIGHT REJECTED	99%	99%	99%	99%
SHADING COEFFICIENT	.51	.52	.59	.64
SOLAR ENERGY REFLECTED	57%	55%	49%	44%
WARRANTY	LIFETIME	LIFETIME	LIFETIME	LIFETIME

